

Lead-free product list

Copper Alloy UNS No.	Cu (%)	Pb (%)	Sn (%)	Zn (%)	Fe (%)	P (%)	Ni (%) ³	Al (%)	Bi (%)	Mn (%)	S (%)	Sb (%)	Si (%)
C69300 ¹	73.00-77.00	0.02 ⁴ -0.09	0.20	Rem.	0.10	0.04-0.15	0.10			0.10		0.10	2.70-3.40
C87850	75.00-78.00	0.02 ⁴ -0.09	0.30	Rem.	0.10	0.05-0.20	0.20			0.10		0.10	2.70-3.40
C89325	84.00-88.00	0.10	9.00-11.00	1.00	0.15	0.10	1.00	0.005	2.70-3.70		0.08	0.50	0.005
C89831	87.00-91.00	0.10	2.70-3.70	2.00-4.00	0.30	0.05	1.00	0.005	2.70-3.70		0.08	0.25	0.005
C89833	86.00-91.00	0.09	4.00-6.00	2.00-6.00	0.30	0.05	1.00	0.005	1.70-2.70		0.08	0.25	0.005
C89835*	85.00-89.00	0.09	6.00-7.50	2.00-4.00	0.20	0.10	1.00	0.005	1.70-2.70		0.08	0.35	0.005
C89844	83.00-86.00	0.20	3.00-5.00	7.00-10.00	0.30	0.05	1.00	0.005	2.00-4.00		0.08	0.25	0.005
C90300*	86.00-89.00 ¹	0.30	7.50-9.00	3.00-5.00	0.20	1.50	1.00	0.005			0.05	0.20	0.005
C90800	85.00-90.00 ¹	0.25	11.00-13.00	0.25	0.15	0.30	0.50	0.005			0.05	0.20	0.005
C90810	Rem. ¹	0.25	11.00-13.00	0.30	0.15	0.15-0.80 ²	0.50	0.005			0.05	0.20	0.005
C95400 ^{5*}	83.00 min				3.00-5.00		1.50	10.00-11.50		0.50			
C95500 ^{5*}	78.00 min				3.00-5.00		3.00-5.50	10.00-11.50		3.50			
C95900	Rem.				3.00-5.00		0.50	12.00-13.50		1.50			

¹Lead-Free Brass *Standard-stocked alloy. ⁴In determining Cu min., Cu may be calculated as Cu + Ni.

²For continuous castings, P shall be 1.5%, max. ³Ni value includes Co. ⁴Pb content is greater than 0.02%.

⁵Also available in heat-treated condition.

Note: Unless otherwise noted, single values represent maximums.